X80 GRADE FOR RISERS AND FLOWLINES







X80 ENABLES A MORE COST-EFFICIENT CONFIGURATION

AN OPERATOR WAS PLANNING AN OFFSHORE PROJECT WITH A RISER MADE OF 41 MM-THICK PIPES IN X65 STEEL.

This would require the use of buoyancy modules in what is known as a steel lazy wave riser (SLWR) configuration.

By replacing the X65 grade with X80, the operator was able to reduce the wall thickness of the riser pipe to 32 mm. This, in turn, eliminated the need for buoyancy modules.

Thanks to this steel catenary riser configuration (SCR), the X80 helps to lower project installation costs. The reduced wall thickness helped the operator eliminate more than 2,000 tons of steel production, which translated to cost savings of around \$2,800/ton.

In addition, installation time was shortened by a full 12 days, saving up to 3,500 metric tons of CO₂ emissions, as estimated along the entire value chain (i.e. from the raw material supply to the transport to final destination), according to the EPD International PCR 2012:01 standard (2012).

WITH X80, THE
OPERATOR SAVED
OVER 2,000 TONS OF
STEEL, LOWERING
INSTALLATION COSTS
AND CO₂ EMISSIONS





UNPARALELLED PERFORMANCE IN ANY ULTRA-DEEPWATER ENVIRONMENT

ONE LINE PIPE X80 DESIGN FOR MILD AND INTERMEDIATE SOUR CONDITIONS

Over the last 10 years, Vallourec has developed and optimized the X80 in close collaboration with end users as well as with engineering, procurement and construction (EPC) partners to deliver proven performance in the mild and intermediate sour environments of NACE regions 1 and 2.

X80 FOR SOUR SERVICE APPLICATIONS

Seamless pipe body:

- Resistant to Mild and Intermediate
 Sour environments (NACE Regions 1 & 2).
- O Hardness below 290 HV10 (as per DNV-ST-F101).
- Average toughness 300J at -30°C.
- Range: OD 219.1-406.4 mm (NPS 8-16"),
 WT up to 40 mm (1.57").
- Possible use of grade X80 for Mechanically Lined Pipes to withstand the most corrosive environments.

Girth welds:

- Resistant to Mild and Intermediate
 Sour environments (NACE Regions 1 & 2).
- Hardness in Heat Affected Zone (HAZ) below 300 HV10.
- No SSC cracks at pH 5.0/2 psi H₂S/85% SMYS (NACE TM0177 Solution B) when testing four-point bend specimens with root left intact as per NACE TM 0316.
- Fatigue results in air exceeding BS 7608 class E target curve.
- Fatigue results in mild sour condition at pH 5.9/0.1 psi H₂S (NACE Region 1) comparable to X65.



PERFORMANCE IN SOUR SERVICE CONDITIONS



REASONS TO CHOOSE THE X80

The X80 not only makes complex ultra-deepwater projects simpler to realize and execute; it also makes them faster, less costly and more ecologically responsible.

BENEFITS OF THE X80 DESIGN



LIGHTER WALL THICKNESS

X80 allows thousands of tons of steel to be saved and therefore reduces CO₂ emissions.



REDUCED WEIGHT

Lighter pipes mean fewer buoyancy modules are needed, decreasing overall project costs.



GREATER FLEXIBILITY


X80 delivers greater pipelaying flexibility on the installation vessel, reducing the number of installation days required.



DESIGNED FOR RAPID WELDING

THE WELDABILITY OF THE X80 IS WIDELY RECOGNIZED BY EPCS AND PROVEN IN TESTS AND IN THE FIELD.

- All welding can be performed using Gas Metal Arc Welding process at a minimum preheating temperature of 125° C.
- Hardness Survey proves structural integrity as per DNV-ST-F101 (Vickers method, 10 kg load).
- Overmatching is achieved with an optimized combination of filler material and pre-heat temperatures.



IN-DEPTH TESTING
CONFIRMS EXCEPTIONAL
PERFORMANCE
IN SOUR SERVICE
ENVIRONMENTS

YOUR PARTNER, SETTING THE PACE FOR INNOVATION AND PERFORMANCE EVOLUTION



NEED MORE INFORMATION?

Information is available online on vallourec.com or by scanning the following QR code.







contact@vallourec.com Headquarters

12, rue de la Verrerie 92190 Meudon - FRANCE Phone: +33 1 49 09 35 00 www.vallourec.com